

# Product of the month

July 2011

## Tumbled Facing Brick

All technical data quoted for this product are the results of independent tests carried out by CERAM Research Ltd in the UK.

<b>Manufacture:</b>	Manufactured in accordance with BS EN 771-3: 2003
<b>Accreditation:</b>	ISO 9001
<b>Dimensions:</b>	215 x 102.5 x 65mm
<b>Weight:</b>	2.5 Kg per brick
<b>Density:</b>	2100 Kg/m <sup>3</sup>
<b>Tolerance/Range:</b>	T2/R1
<b>Compressive Strength:</b>	75M/mm <sup>2</sup>
<b>Water Absorption:</b>	≤7.0%
<b>Active Soluble Salts:</b>	82
<b>Frost Resistance:</b>	F2
<b>Thermal Conductivity:</b>	0.63 W/m.K
<b>Reaction to Fire:</b>	Class A1
<b>Bond Strength:</b>	0.15 N/mm <sup>2</sup>
<b>Weight of Pack:</b>	Average Weight of Pack 1.3 tonne. (Sq) 1.25 (Tum)
<b>Bricks per Pack:</b>	520 No



**Call now**  
for competitive prices

Building - Northampton

**01604 417930**

email [buildingnorthampton@hevey.co.uk](mailto:buildingnorthampton@hevey.co.uk)