

Tumbled Facing Brick

All technical data quoted for this product are the results of independent tests carried out by CERAM Research Ltd in the UK.

Manufacture:	Manufactured in accordance with BS EN 771-3: 2003
Accreditation:	ISO 9001
Dimensions:	215 x 102.5 x 65mm
Weight:	2.5 Kg per brick
Density:	2100 Kg/m ³
Tolerance/Range:	T2/R1
Compressive Strength:	75M/mm ²
Water Absorption:	≤7.0%
Active Soluble Salts:	82
Frost Resistance:	F2
Thermal Conductivity:	0.63 W/m.K
Reaction to Fire:	Class A1
Bond Strength:	0.15 N/mm ²
Weight of Pack:	Average Weight of Pack 1.3 tonne. (Sq) 1.25 (Tum)
Bricks per Pack:	520 No



Call now
for competitive prices

Building - Northampton

01604 417930

email buildingnorthampton@hevey.co.uk